



SHANGHAI NYTEX COMPOSITES

TEL:021-59573168 FAX:021-59573707
http://www.nytex.com.cn

Product Information

NYLOY[®] MG-8030N-V 60N1

- Nylon 66
- 34% Glass Fiber Reinforced / Non-Halogen Flame Retardant
- Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ISO 527	MPa	125
Elongation	ISO 527	%	2
Flexural Strength	ISO 178	MPa	185
Flexural Modulus	ISO 178	MPa	9000
Charpy Impact, Notched 23° C	ISO 179/ 1eA	kJ/m ²	6.5
Charpy Impact, Notched -20°C	ISO 179/ 1eA	kJ/m ²	-
Hardness Rockwell R Scale	ISO 2039	-	-
Hardness Shore D	ISO 868	-	-
THERMAL			
Heat Deflection Temp	ISO 75		
1.82MPa		°C	230
0.46MPa		°C	-
OTHER			
Density	ISO 1183	g/cm ³	1.43
Mold Shrinkage	ISO 294-4		-
Normal		%	1.28
Parallel		%	0.48
Ash Content	-	%	35
Flammability	UL-94	1.6mm	V0
	UL-94	3.2mm	-
REMARK			
(1) This data is for reference only.			