



SHANGHAI NYTEX COMPOSITES

TEL:021-59573168 FAX:021-59573707
http://www.nytex.com.cn

Product Information

NYLOY[®] MG-8030N-V 60BK2

- Nylon 66
- 30% Glass Fiber Reinforced/Non-Halogen Flame Retardant
- Black

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	kg/cm ² (MPa)	1150 (112.86)
Elongation	ASTM D638	%	2
Flexural Strength	ASTM D790	kg/cm ² (MPa)	1750 (171.74)
Flexural Modulus	ASTM D790	kg/cm ² (MPa)	8.50x10 ⁴ (8341.51)
IZOD Impact, Notched 1/8" 23°C	ASTM D256	kg-cm/cm (J/M)	6.0 (58.82)
IZOD Impact, Notched 1/8" -20°C	ASTM D256	kg-cm/cm (J/M)	-
Hardness Rockwell R Scale	ASTM D785	-	-
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
(18.6kg/cm ²) (1.82MPa)		°C	230
(4.6kg/cm ²) (0.46MPa)		°C	-
ELECTRICAL			
Arc Resistance	ASTM D495	sec	-
CTI,solution A	IEC 60112	-	425
OTHER			
Density	ASTM D792	g/cm ³	1.47
Mold Shrinkage ⁽²⁾	ASTM D955	x10 ⁻³ mm/mm	2.5-3.5
Moisture Contents	-	%	0.2
Flammability	UL-94	1.6mm	V0
	UL-94	3.2mm	-
REMARK			
⁽¹⁾ This data is for reference only.			
⁽²⁾ Shrinkage parallel to flow. Test box dimensions of base(129×2.7×3.2) mm.			