



SHANGHAI NYTEX COMPOSITES

TEL:021-59573168 FAX:021-59573707
http://www.nytex.com.cn

Product Information

NYLOY[®] MG-8030N-V 60BK2

- Nylon 66
- 30% Glass Fiber Reinforced/Non-Halogen Flame Retardant
- Black

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	psi	16358.46
Elongation	ASTM D638	%	2
Flexural Strength	ASTM D790	psi	24893.31
Flexural Modulus	ASTM D790	psi	1209103.84
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	1.1
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	-
Hardness Rockwell R Scale	ASTM D785	-	-
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
264 psi		°F	446
66 psi		°F	-
ELECTRICAL			
Arc Resistance	ASTM D495	sec	-
CTI,solution A	IEC 60112	-	425
OTHER			
Density	ASTM D792	lb/in ³	0.0456
Mold Shrinkage ⁽²⁾	ASTM D955	x10 ⁻³ in/in	2.5-3.5
Moisture Contents	-	%	0.2
Flammability	UL-94	1/16 in	V0
	UL-94	1/8 in	-
REMARK			
(1) This data is for reference only.			
(2) Shrinkage parallel to flow. Test box dimensions of base(129×2.7×3.2) mm.			