



# SHANGHAI NYTEX COMPOSITES

TEL:021-59573168 FAX:021-59573707  
http://www.nytex.com.cn

## Product Information

## NYLOY<sup>®</sup> MG-0833B

- Nylon 66 • 33%Glass Fiber Reinforced • Black

PROPERTY	METHOD	UNIT	RESULT
<b>MECHANICAL</b>			
Tensile Strength	ASTM D638	psi	19914.65
Elongation	ASTM D638	%	2
Flexural Strength	ASTM D790	psi	28449.5
Flexural Modulus	ASTM D790	psi	1137980.09
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	1.47
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	-
Hardness Rockwell R Scale	ASTM D785	-	-
Hardness Shore D	ASTM D2240	-	-
<b>THERMAL</b>			
Heat Deflection Temp	ASTM D648		
264 psi		°F	437
66 psi		°F	455
<b>OTHER</b>			
Density	ASTM D792	lb/in <sup>3</sup>	0.0428
Mold Shrinkage	ASTM D955		-
Normal		%	1.03
Parallel		%	0.34
Moisture Contents	-	%	-
Flammability	UL-94	1/16 in	HB
	UL-94	1/8 in	-
<b>REMARK</b>			
(1) This data is for reference only.			