



SHANGHAI NYTEX COMPOSITES

TEL:021-59573168 FAX:021-59573707
http://www.nytex.com.cn

Product Information

NYLOY® NG-0033N

• Nylon 6 • 33% Glass Fiber Reinforced • Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	kg/cm ² (MPa)	1800 (176.64)
Elongation	ASTM D638	%	2.5
Flexural Strength	ASTM D790	kg/cm ² (MPa)	2600 (255.15)
Flexural Modulus	ASTM D790	kg/cm ² (MPa)	1.05x10 ⁵ (10304.22)
IZOD Impact, Notched 1/8" 23°C	ASTM D256	kg-cm/cm (J/M)	16.0 (156.86)
IZOD Impact, Notched 1/8" -20°C	ASTM D256	kg-cm/cm (J/M)	-
Hardness Rockwell R Scale	ASTM D785	-	R-114
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
(18.6kg/cm ²) (1.82MPa)		°C	210
(4.6kg/cm ²) (0.46MPa)		°C	-
OTHER			
Density	ASTM D792	g/cm ³	1.384
Mold Shrinkage	ASTM D955		-
Normal		%	0.93
Parallel		%	0.34
Moisture Contents	-	%	-
REMARK			
(1) This data is for reference only.			