



SHANGHAI NYTEX COMPOSITES

TEL:021-59573168 FAX:021-59573707
http://www.nytex.com.cn

Product Information

NYLOY[®] NG-0033N

• Nylon 6 • 33% Glass Fiber Reinforced • Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	psi	25604.55
Elongation	ASTM D638	%	2.5
Flexural Strength	ASTM D790	psi	36984.35
Flexural Modulus	ASTM D790	psi	1493598.86
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	2.94
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	-
Hardness Rockwell R Scale	ASTM D785	-	R-114
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
264 psi		°F	410
66 psi		°F	-
OTHER			
Density	ASTM D792	lb/in ³	0.0429
Mold Shrinkage	ASTM D955		-
Normal		%	0.93
Parallel		%	0.34
Moisture Contents	-	%	-
REMARK			
(1) This data is for reference only.			