



# SHANGHAI NYTEX COMPOSITES

TEL:021-59573168 FAX:021-59573707  
http://www.nytex.com.cn

## Product Information

## NYLOY<sup>®</sup> MG-0025N-V0

- Nylon66
- Glass Fiber Reinforced/Flame Retardant
- White

PROPERTY	METHOD	UNIT	RESULT
<b>MECHANICAL</b>			
Tensile Strength	ASTM D638	psi	18492.18
Elongation	ASTM D638	%	2
Flexural Strength	ASTM D790	psi	27027.03
Flexural Modulus	ASTM D790	psi	1209108
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	1.38
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	-
Hardness Rockwell R Scale	ASTM D785	-	-
Hardness Shore D	ASTM D2240	-	-
<b>THERMAL</b>			
Heat Deflection Temp	ASTM D648		
264 psi		°F	446
66 psi		°F	-
<b>ELECTRICAL</b>			
Arc Resistance	ASTM D495	sec	-
CTI,solution A	IEC 60112	-	-
<b>OTHER</b>			
Density	ASTM D792	lb/in <sup>3</sup>	0.0476
Mold Shrinkage <sup>(2)</sup>	ASTM D955	-	-
Moisture Contents	-	%	-
Flammability	UL-94	1/16 in	-
	UL-94	1/8 in	V0
<b>REMARK</b>			
<sup>(1)</sup> This data is for reference only.			
<sup>(2)</sup> Shrinkage parallel to flow. Test box dimensions of base(129×2.7×3.2) mm.			