



SHANGHAI NYTEX COMPOSITES

TEL:021-59573168 FAX:021-59573707

<http://www.nytex.com.cn>

Product Information

NYLOY[®] UG-0030N-V0 6T NL

- PA6T
- 30% glass fiber reinforced / flame retardant
- Natural

PROPERTIES	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ISO 527	MPa	200
Elongation	ISO 527	%	2.0
Flexural Strength	ISO 178	MPa	285
Flexural Modulus	ISO 178	MPa	11000
Charpy Impact, Notched 23° C	ISO 179/2-1eU	kJ/m ²	8.5
Charpy Impact, Notched -30°C	ISO 179/2-1eU	kJ/m ²	8.5
Hardness Rockwell R Scale	ISO 2039	-	-
THERMAL			
Heat Deflection Temp 1.8 MPa	ISO 75	°C	285
OTHER			
Specific Gravity	ISO 1183	g/cm ³	1.62
Mold Shrinkage	ISO 294		
Normal		%	-
Parallel		%	-
Flammability	UL-94	0.8mm	V0
REMARK			
(1) This data is for reference only .			

Moulding guide

Drying Temp.	°C	100~120
Drying Time	hr	4~12
Mold Temp.	°C	115
1 st inj.		
V(%) / P(%)	%	75/65
2 nd inj.		
V(%) / P(%)	%	65/55
3 rd inj.		
V(%) / P(%)	%	55/45
4 th inj.		
V(%) / P(%)	%	35/20
Nozzle Temp.	°C	320
1 st Barrel Temp.	°C	320
2 nd Barrel Temp.	°C	320
3 rd Barrel Temp.	°C	300
Cooling Time	Sec.	16

REMARK

This data-sheet is for reference only.