



SHANGHAI NYTEX COMPOSITES

TEL:021-59573168 FAX:021-59573707
http://www.nytex.com.cn

Product Information

NYLOY® CT-0020N-V R601B

●PC

●Electrical Insulative
Thermal Conductive
Flame Retardant & Weather Resistance(f1)

●Black

PROPERTIES	測試方法 METHOD	單位 UNIT	結果(數據) RESULT	
MECHANICAL				
Tensile Strength	ASTM D638	kg/cm ² (MPa)	410	(40)
Elongation	ASTM D638	%	8	
Flexural Strength	ASTM D790	kg/cm ² (MPa)	800	(79)
Flexural Modulus	ASTM D790	kg/cm ² (MPa)	34000	(3337)
Izod Impact, Notched 1/8" 23°C	ASTM D256	Kg-cm/cm (J/M)	7	(69)
THERMAL				
Heat Deflection Temp (4.6kg/cm ²) (0.45MPa)	ASTM D648	°C	105	
Thermal Conductivity	ISO 22007-2	W/m*K	0.7	
OTHER				
Density	ASTM D792	g/cm ³	1.41	
Mold Shrinkage	ASTM D955	%	0.2-0.6	
Drop ball test	Nytex Method(*)		Pass	
Flammability	UL-94	1.6 mm	V0	
ELECTRICAL				
Surface Resistance	IEC 60093	Ohm-P-SQ	> 1E+12	
REMARK				
(1) This data is for reference only . The size of the falling drop ball test specimen is 150*150*1.6mm. The test conditions use a 500G Iron ball to be freely dropped from a height of 130cm.				

Moulding guide

Drying Temp.	°C	100
Drying Time	hr	2~4
Mold Temp.	°C	80
1 st inj.		
V(%)/P(%)	%	85/75
2 nd inj.		
V(%)/P(%)	%	60/50
3 rd inj.		
V(%)/P(%)	%	30/20
4 th inj.		
V(%)/P(%)	%	20/10
Nozzle Temp.		
	°C	310~290
1 st Barrel Temp.		
	°C	295~275
2 nd Barrel Temp.		
	°C	285~265
3 rd Barrel Temp.		
	°C	250~230
Cooling Time	Sec.	25

REMARK

This data-sheet is for reference only.