



SHANGHAI NYTEX COMPOSITES

TEL:021-59573168 FAX:021-59573707
http://www.nytex.com.cn

Product Information

NYLOY[®]UB-0010N G60L2B

• High Temp. Nylon • Glass Fiber Reinforced • Black

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ISO 527	MPa	245
Elongation	ISO 527	%	1.7
Flexural Strength	ISO 178	MPa	340
Flexural Modulus	ISO 178	MPa	18900
Charpy Impact, Notched 23° C	ISO 179	kJ/M ²	14
THERMAL			
Heat Deflection Temp (18.6kg/cm ²)(1.82MPa)	ISO 75	°C	235
OTHER			
Ash Contents	ISO 3451	%	GF 60
Flammability	UL-94	1.6mm	-
	UL-94	0.8mm	-
Density	ISO 1183	g/cm ³	1.71
PHYSICAL			
Mold Shrinkage	ISO 294-4		-
	Normal	%	0.4
	Parallel	%	0.25
FLAMMABILITY			
Glow Wire Test(GWFI)	IEC 60695-2-12	2.0mm	-
Glow Wire Test(GWIT)	IEC 60695-2-13	2.0mm	-
ELECTRICAL			
CTI(Solution A)	IEC 60112		-
REMARK			
(1)This data is for reference only.			