



SHANGHAI NYTEX COMPOSITES

TEL:021-59573168 FAX:021-59573707
http://www.nytex.com.cn

Product Information

NYLOY[®]UB-0010N-V G30N4N

- High Temp. Nylon
- Glass Fiber Reinforced / Non-Halogen Flame Retardant
- Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ISO 527	MPa	160
Elongation	ISO 527	%	2.5
Flexural Strength	ISO 178	MPa	240
Flexural Modulus	ISO 178	MPa	9200
Charpy Impact, Notched 23° C	ISO 179	kJ/M ²	8
THERMAL			
Heat Deflection Temp (18.6kg/cm ²)(1.82MPa)	ISO 75	°C	270
OTHER			
Ash Contents	ISO 3451	%	GF 30
Flammability	UL-94	1.6mm	V0
	UL-94	0.8mm	V0
Density	ISO 1183	g/cm ³	1.42
PHYSICAL			
Mold Shrinkage	ISO 294-4		-
	Normal	%	0.95
	Parallel	%	0.34
FLAMMABILITY			
Glow Wire Test(GWFI)	IEC 60695-2-12	2.0mm	960
Glow Wire Test(GWIT)	IEC 60695-2-13	2.0mm	775
ELECTRICAL			
CTI(Solution A)	IEC 60112		600
REMARK			
(1)This data is for reference only.			