



# SHANGHAI NYTEX COMPOSITES

TEL:021-59573168 FAX:021-59573707  
http://www.nytex.com.cn

## Product Information

## NYLOY<sup>®</sup> UB-0010N G50L2N

• High Temp. Nylon • Glass Fiber Reinforced • Natural

PROPERTY	METHOD	UNIT	RESULT
<b>MECHANICAL</b>			
Tensile Strength	ISO 527	MPa	220
Tensile Modulus	ISO 527	MPa	-
Elongation	ISO 527	%	2
Flexural Strength	ISO 178	MPa	320
Flexural Modulus	ISO 178	MPa	14300
Charpy Impact, Notched 23° C	ISO 179	kJ/M <sup>2</sup>	14
<b>THERMAL</b>			
Heat Deflection Temp (18.6kg/cm <sup>2</sup> )(1.82MPa)	ISO 75	°C	245
<b>OTHER</b>			
Ash Contents	ISO 3451	%	GF 50
Flammability	UL-94	1.6mm	-
	UL-94	0.8mm	-
Density	ISO 1183	g/cm <sup>3</sup>	1.58
<b>PHYSICAL</b>			
Mold Shrinkage	ISO 294-4		-
Normal		%	0.46
Parallel		%	0.29
<b>FLAMMABILITY</b>			
Glow Wire Test(GWFI)	IEC 60695-2-12	2.0mm	-
Glow Wire Test(GWIT)	IEC 60695-2-13	2.0mm	-
<b>REMARK</b>			
(1)This data is for reference only.			