



SHANGHAI NYTEX COMPOSITES

TEL:021-59573168 FAX:021-59573707
http://www.nytex.com.cn

Product Information

NYLOY[®] UB-0010N G50N1N

• High Temp. Nylon • Glass Fiber Reinforced • Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ISO 527	MPa	220
Tensile Modulus	ISO 527	MPa	-
Elongation	ISO 527	%	2
Flexural Strength	ISO 178	MPa	340
Flexural Modulus	ISO 178	MPa	13900
Charpy Impact, Notched 23° C	ISO 179	kJ/M ²	12
THERMAL			
Heat Deflection Temp (18.6kg/cm ²)(1.82MPa)	ISO 75	°C	245
OTHER			
Ash Contents	ISO 3451	%	GF 50
Flammability	UL-94	1.6mm	-
	UL-94	0.8mm	-
Density	ISO 1183	g/cm ³	1.57
PHYSICAL			
Mold Shrinkage	ISO 294-4		-
Normal		%	0.63
Parallel		%	0.33
FLAMMABILITY			
Glow Wire Test(GWFI)	IEC 60695-2-12	2.0mm	-
Glow Wire Test(GWIT)	IEC 60695-2-13	2.0mm	-
REMARK			
(1)This data is for reference only.			