



SHANGHAI NYTEX COMPOSITES

TEL:021-59573168 FAX:021-59573707
http://www.nytex.com.cn

Product Information

NYLOY® NF-0035B-S

• Nylon 6 • 35% Mineral Reinforced • Black

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	psi	9246.09
Elongation	ASTM D638	%	5.5
Flexural Strength	ASTM D790	psi	14224.75
Flexural Modulus	ASTM D790	psi	512091.04
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	1.1
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	-
Hardness Rockwell R Scale	ASTM D785	-	-
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
264 psi		°F	158
66 psi		°F	374
ELECTRICAL			
Arc Resistance	ASTM D495	sec	-
CTI,solution A	IEC 60112	-	-
OTHER			
Density	ASTM D792	lb/in ³	0.0440
Mold Shrinkage ⁽²⁾	ASTM D955	x10 ⁻³ in/in	12-16
Moisture Contents	-	%	0.2
Flammability	UL-94	1/16 in	HB
	UL-94	1/8 in	-
REMARK			
⁽¹⁾ This data is for reference only.			
⁽²⁾ Shrinkage parallel to flow. Test box dimensions of base(129×2.7×3.2) mm.			