



SHANGHAI NYTEX COMPOSITES

TEL:021-59573168 FAX:021-59573707
http://www.nytex.com.cn

Product Information

NYLOY[®] KM-21SPC

• Nylon 66 • General Grade • Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	kg/cm ² (MPa)	780 (76.55)
Elongation	ASTM D638	%	50
Flexural Strength	ASTM D790	kg/cm ² (MPa)	-
Flexural Modulus	ASTM D790	kg/cm ² (MPa)	-
IZOD Impact, Notched 1/8" 23°C	ASTM D256	kg-cm/cm (J/M)	5.5 (53.92)
IZOD Impact, Notched 1/8" -20°C	ASTM D256	kg-cm/cm (J/M)	-
Hardness Rockwell R Scale	ASTM D785	-	-
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
(18.6kg/cm ²) (1.82MPa)		°C	-
(4.6kg/cm ²) (0.46MPa)		°C	-
ELECTRICAL			
Arc Resistance	ASTM D495	sec	-
CTI,solution A	IEC 60112	-	600
OTHER			
Density	ASTM D792	g/cm ³	1.13
Mold Shrinkage ⁽²⁾	ASTM D955	x10 ⁻³ mm/mm	15-25
Moisture Contents	-	%	0.2
Flammability	UL-94	1.6mm	V2
	UL-94	3.2mm	-
REMARK			
⁽¹⁾ This data is for reference only.			
⁽²⁾ Shrinkage parallel to flow. Test box dimensions of base(129×2.7×3.2) mm.			