



SHANGHAI NYTEX COMPOSITES

TEL:021-59573168 FAX:021-59573707
http://www.nytex.com.cn

Product Information

NYLOY[®] RM-100-C

- Nylon 66
- General Grade
- Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	psi	11095.31
Elongation	ASTM D638	%	50
Flexural Strength	ASTM D790	psi	-
Flexural Modulus	ASTM D790	psi	-
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	1.01
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	-
Hardness Rockwell R Scale	ASTM D785	-	-
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
264 psi		°F	-
66 psi		°F	-
ELECTRICAL			
Arc Resistance	ASTM D495	sec	-
CTI,solution A	IEC 60112	-	600
OTHER			
Density	ASTM D792	lb/in ³	0.0350
Mold Shrinkage ⁽²⁾	ASTM D955	x10 ⁻³ in/in	15-25
Moisture Contents	-	%	0.2
Flammability	UL-94	1/16 in	V2
	UL-94	1/8 in	-
REMARK			
⁽¹⁾ This data is for reference only.			
⁽²⁾ Shrinkage parallel to flow. Test box dimensions of base(129×2.7×3.2) mm.			