



# SHANGHAI NYTEX COMPOSITES

TEL:021-59573168 FAX:021-59573707

<http://www.nytex.com.cn>

## Product Information

## NYLOY<sup>®</sup> MS-0020N-1

• Nylon 66 • Impact Modified • Natural

PROPERTY	METHOD	UNIT	RESULT
<b>MECHANICAL</b>			
Tensile Strength	ASTM D638	kg/cm <sup>2</sup> (MPa)	450 (44.16)
Elongation	ASTM D638	%	105
Flexural Strength	ASTM D790	kg/cm <sup>2</sup> (MPa)	600 (58.88)
Flexural Modulus	ASTM D790	kg/cm <sup>2</sup> (MPa)	1.60x10 <sup>4</sup> (1570.17)
IZOD Impact, Notched 1/8" 23°C	ASTM D256	kg-cm/cm (J/M)	110.0 (1078.43)
IZOD Impact, Notched 1/8" -20°C	ASTM D256	kg-cm/cm (J/M)	90 (822.35)
Hardness Rockwell R Scale	ASTM D785	-	-
Hardness Shore D	ASTM D2240	-	D-71
<b>THERMAL</b>			
Heat Deflection Temp	ASTM D648		
(18.6kg/cm <sup>2</sup> ) (1.82MPa)		°C	-
(4.6kg/cm <sup>2</sup> ) (0.46MPa)		°C	-
<b>ELECTRICAL</b>			
Arc Resistance	ASTM D495	sec	-
CTI,solution A	IEC 60112	-	-
<b>OTHER</b>			
Density	ASTM D792	g/cm <sup>3</sup>	1.072
Mold Shrinkage	ASTM D955		-
Normal		%	1.81
Parallel		%	1.53
Moisture Contents	-	%	-
Flammability	UL-94	1.6mm	-
	UL-94	3.2mm	-
<b>REMARK</b>			
<sup>(1)</sup> This data is for reference only.			